

Flexible rubber magnet

Physical performance of Flexible rubber magnet							
Category	Grade	Remanence	Coercivity	Intrinsic Coercivity	Maximum Energy Product	Material	Producing way
glue magnet of the same nature	YNT-4	135-155(1350-1550)	85-105(1050-1300)	175-210(2200-2600)	3.2-5.0(0.40-0.62)	BaO.6Fe ₂ O ₃ SrO.6Fe ₂ O ₃	rolling process
	YNT-S5	165-180(1650-1800)	90-105(1130-1300)	135-160(1700-2010)	4.5-5.8(0.56-0.72)		
	YNT-B5	170-190(1700-1900)	90-115(1200-1450)	150-190(1885-2400)	4.6-6.5(0.57-0.80)		
	YNT-6.5	185-200(1850-2000)	90-110(1130-1380)	125-150(1570-1885)	6.0-7.0(0.74-0.93)		
Heterosexual glue magnet	YNY-10	220-240(2200-2400)	140-165(1760-2070)	200-235(2500-2950)	9.0-10.5(1.1-1.30)	SrO.6Fe ₂ O ₃	rolling process
	YNY-11	230-250(2300-2500)	145-165(1820-2070)	190-225(2380-2850)	9.5-11.0(1.18-1.36)		
	YNY-13	250-270(200-2700)	175-190(2200-2400)	200-230(2500-2900)	11.5-14.5(1.42-1.80)		
	YNY-15	≥270(≥2700)	175-190(2200-2400)	200-230(2500-2900)	≥14.5(≥1.8)		